












			CREATION MINERAL
DESCRIPTION			
Total thickness	EN 428	mm	2,5
Thickness of wearlayer	EN 429	mm	0,7
Weight	EN 430	g/m ²	4400
Tile size	EN 427	mm	
Plank size	EN 427	mm	228.6 x 457
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	<2
Slip resistance wet: ramp test with oil	DIN 51130	class	R9
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤0,08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤0,15
Residual indentation	EN 433	mm	≤0,1
Impact sound insulation	EN ISO 717-2	dB	
Thermal conductivity	EN 12524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥6
Chemical products resistance	EN 423	-	OK
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		   

			CREATION MINERAL
DESCRIPTION			
Total thickness	EN 428	mm	2,5
Thickness of wearlayer	EN 429	mm	0,7
Weight	EN 430	g/m ²	4400
Tile size	EN 427	mm	
Plank size	EN 427	mm	457 x 457
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet: ramp test with oil	DIN 51130	class	R9
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0,08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0,15
Residual indentation	EN 433	mm	≤ 0,1
Impact sound insulation	EN ISO 717-2	dB	
Thermal conductivity	EN 12524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		   

			CREATION MINERAL PEEBLE
DESCRIPTION			
Total thickness	EN 428	mm	2,5
Thickness of wearlayer	EN 429	mm	0,7
Weight	EN 430	g/m ²	4400
Tile size	EN 427	mm	
Plank size	EN 427	mm	457 x 457
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet: ramp test with oil	DIN 51130	class	R9
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0,08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0,15
Residual indentation	EN 433	mm	≤ 0,1
Impact sound insulation	EN ISO 717-2	dB	
Thermal conductivity	EN 12524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		