























			TARALAY PREMIUM INDIANA COMPACT
DESCRIPTION			
Total thickness	EN 428	mm	2
Thickness of wearlayer	EN 429	mm	≥ 1.00
Weight	EN 430	g/m ²	2680
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
Classification K	-	class	
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	< = 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	
Surface treatment			Protecsol®
MARQUAGE CE			
	EN 14041		   

TARALAY PREMIUM COSTA RICA COMPACT			
DESCRIPTION			
Total thickness	EN 428	mm	2
Thickness of wearlayer	EN 429	mm	≥ 1.00
Weight	EN 430	g/m ²	2580
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
Classification K	-	class	
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	
Surface treatment	-	-	Protecsol®
MARQUAGE CE			
	EN 14041		   

TARALAY PREMIUM BRAZILIA COMPACT			
DESCRIPTION			
Total thickness	EN 428	mm	2
Thickness of wearlayer	EN 429	mm	≥ 1,00
Weight	EN 430	g/m ²	2580
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
Classification K	-	class	
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0,10
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	
Surface treatment	-	-	Protecsol®
MARQUAGE CE			
	EN 14041		   

TARALAY PREMIUM METALLICA COMPACT			
DESCRIPTION			
Total thickness	EN 428	mm	2
Thickness of wearlayer	EN 429	mm	≥ 1.00
Weight	EN 430	g/m ²	2620
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
Classification K	-	class	
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	
Surface treatment	-	-	Protecsol®
MARQUAGE CE			
	EN 14041		   

			TARALAY PREMIUM FUSION COMPACT
DESCRIPTION			
Total thickness	EN 428	mm	2
Thickness of wearlayer	EN 429	mm	≥ 1.00
Weight	EN 430	g/m ²	2650
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
Classification K	-	class	
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	
Surface treatment	-	-	Protecsol®
MARQUAGE CE			
	EN 14041		   

			TARALAY PREMIUM FORUM COMPACT
DESCRIPTION			
Total thickness	EN 428	mm	2
Thickness of wearlayer	EN 429	mm	≥ 1.00
Weight	EN 430	g/m ²	2580
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
Classification K	-	class	
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	
Surface treatment	-	-	Protecsol®
MARQUAGE CE			
	EN 14041		   

DESCRIPTION

Total thickness	EN 428	mm	2
Thickness of wearlayer	EN 429	mm	≥ 1.00
Weight	EN 430	g/m ²	2550
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20




CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
Fire rating	EN 13 501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2

PERFORMANCE

Wear resistance	EN 660-1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	Protecsol®

CE MARKING

	EN 14041	-	
		-	

DESCRIPTION

Total thickness	EN 428	mm	2
Thickness of wearlayer	EN 429	mm	≥ 1.00
Weight	EN 430	g/m ²	2800
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20



CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
Fire rating	EN 13 501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2

PERFORMANCE

Wear resistance	EN 660-1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	Protecsol®

CE MARKING

	EN 14041	-	
		-	